

HARDWAXOIL MAGIC



Modified parquet oil with excellent wear resistance. Good filling, natural color, and excellent chemical and mechanical resistance. Gives a very matte finish. The resistance can be further improved by adding a UA hardener.

- » Matte, natural finish that maintains the natural appearance of the wooden surface.
- » Fast-drying.
- » Excellent chemical resistance.

TECHNICAL DATA

Product type

Solvent-based

Cleaning

Cleaning Thinner Ciranova[®]

Mixing ratio

Optional hardener UA: 100/5

Gloss level

Ultra matte

Viscosity

+/- 50 sec - DIN 4mm

Solid content

+/- 47%

Packaging

1 L / 5 L

Number of colors

clear and colorless - satin shine

Coverage

40 - 50 m²/liter per coat
450-550 sq.ft./L per coat
1700 - 2080 sq.ft./gal per coat

Drying times

Recoatable: after +/- 6 hours
Lightly walkable after 24 hours.
Fully cured after +/- 10 days

Sanding grit

P 100-120

Storage/transport

between 5°C and 25°C

Potlife

+/- 3 hours after adding the hardener

Disposal

Dispose of residue and empty packaging in accordance with local ordinances.



PREPARATION

Make sure that all old finish coats are completely removed and that the wood is free from dust and other dirt. Sanding using the correct method : deep sanding with 60-80-100 grit then sanding with 100 grit. Can be used on sanded, planed, and brushed wood. Pre-wetting the wood can give a more intensive stain.

APPLICATION

Stir and shake well before and during use. Apply HARDWAXOIL MAGIC evenly with a buffing machine or a brush. Let the Hardwaxoil Magic settle and remove any excess oil within a few minutes by brushing it with a pad or cloth until the surface feels hand-dry. Hardwood like oak require 2 layers. Multiple layers can be applied for softwood. For exotic wood types, the Hardwaxoil Magic should be tested beforehand. **OPTIONAL: A HARDENER UA (5%) CAN BE ADDED TO INCREASE THE CHEMICAL AND MECHANICAL RESISTANCES.** For industrial applications (rolling, spraying) the Ciranova[®] technical service should be consulted.

FINISHING

A colored oil should subsequently be finished with a layer of Hardwaxoil TITAN [roller application].

MAINTENANCE

For regular maintenance, we recommend Ciranova[®] Flooring Soap. For periodic maintenance, use Ciranova[®] Maintenance Oil or first use Ciranova[®] Intensive Cleaner in case of heavy dirt. Hardwaxoil MAGIC is only fully hardened after +/- 7 days. During this period, the wood cannot be treated with water or maintenance products.

IMPORTANT INFORMATION ⚠

Dried oil residue is self-igniting. Used pads and clothes must be submerged in water after use.

